

X-Pruf RBE

General purpose high build latex enhanced bitumen emulsion

Product Description

X-Pruf RBE is a thixotropic high build bitumen emulsion modified with latex rubber to give enhanced performance.

Advantages

- Cost effective
- Flexible
- Liquid applied
- Environmentally friendly
- Can be applied to green concrete

Uses

- Damp proof membrane
- Curing compound
- Concrete protection
- Bathroom and kitchen waterproofing
- General purpose waterproofing
- Plaster key
- Insulation board adhesive

Specification Compliance

ASTM D2939

Laboratory Test Data

Properties	Values	Test Methods
Form	Thick Viscous Liquid	
Color	Dark Brown	
Specific Gravity	1.03 ± 0.02	ASTM D2939
Solid content [%]	35±5	ASTM D 2939
Drying time [hrs]	24hr	ASTM D2939
Application temp	5 to 45°C	
Heat Test	100 ± 3 no blistering sagging, or slipping	ASTM D2939
Flexibility 0 ± 1°C	No cracking or flaking	ASTM D 2939
Resistance to water 24hr	No blistering or re emulsification	ASTM D2939
Time between two coats	3-4 hr depending on temp.	

Color

Dark Brown

Theoretical Coverage

3 - 4 m²/Kg per coat.

Actual coverage will vary depending on substrate porosity.

Packaging

20 and 200 Kg drums.

Shelf Life

12 months when stored between 5 and 40C under shade in a dry environment.

Installation Guidelines

Surface Preparation

All surfaces to be treated should be clean and free from any contamination or surface water. Hot and porous substrates should be primed with a primer coat of diluting X-Pruf RBE with 15-20% of potable water. Apply to the substrate and allow to absorb and dry before application of the second coat with diluted percentage of 5-10% with potable water. Normally 2 or 3 coats are required depending on degree of protection required.

Application

X-Pruf RBE Membrane can be applied by brush, squeegee or airless spray. Stir well prior to use. It is recommended that one or two coats should be applied depending on the degree of protection required. Allow a minimum of 3 hours drying time between coats. For vertical applications, ensure that no sagging occurs. For multiple coat applications, the second coat should be applied at right angles to the first. All applications should be continued up verticals to the existing damp proof course. Ensure that the membrane is not damaged during subsequent applications. Where X-Pruf RBE Membrane is to receive a screed, two coats should be applied. The second coat should be bladed with clean, dry sharp sand immediately after application. The excess sand should be brushed off when the coating has dried.

Clean Up

Clean tools and equipment with water while still wet. Once dry, remove mechanically or using a suitable solvent.

Limitations

Do not expose to sunlight for long periods.
Do not apply at temperatures below 5C or above 45C.
Do not add solvent.
Avoid skin contact.
Do not discard into the water system.

Health and Safety

This product is for industrial use only by trained operatives. It is potentially hazardous if not used correctly. Please refer to the Material Safety Data Sheet (MSDS) prior to the purchase and use of this product. The MSDS can be obtained via our website www.ncc.com.eg.

Authorized Technical Specialist

Please note that only NCC X-Calibur Authorized Technical Specialists ('ATSS') are permitted to change any of the information in this data sheet or to provide written recommendations concerning the use of this product. Visit www.ncc.com.eg for a full list of NCC X-Calibur ATSS.

Datasheet Validity

NCC X-Calibur makes modifications to its product datasheets on a continuous basis. Check the datasheet update section on www.ncc.com.eg to ensure you have the latest version.

Warranties

NCC X-Calibur supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. NCC X-Calibur does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to NCC X-Calibur in writing within five working days of being detected. NCC X-Calibur Construction Chemicals. **makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied.** NCC X-Calibur Construction Chemicals shall not be liable for damages of any sort including remote or consequential damages, down time, or delay.